



Bodotex Composites
Ferrarivej 4
DK – 7100 Vejle
Denmark
+4576408999
axel@bodotex.dk

Technical Data Sheet

Bodocure CA 43 Medium

Type: Alkylated amine adducts and modified aliphatic polyamine system for epoxy.

Properties: Good curing, even in surroundings with low temperatures

and relatively high humidity. Good adhesion to difficult substrates. Cures from 5-7 °C with quite good mechanical properties, but for the best possible strength, it is recommended to cure at +30-35 °C

Pot life of approx. 35-40 min at 23 °C

Application:

This curing agent has been developed particularly for hand laminations where there is a need for good pot life under difficult conditions such as low temperatures and possibly in humid conditions. Bodopox 5000H or Bodopox 8000 is suitable as epoxy component.

Physical and chemical data:

Viscosity: 100 – 150 mPa*s

Bulk density: 0.99 kg/l

AHEW: approx. 81 g/eq.

Pot life: approx. 40 min (200 g at 20 °C)

Tg: 60-70 °C DSC, 10 °C/min.

Hazard labelling:

Corrosive and hazardous to the environment.

Contact: Bodotex Composites telephone +45 76408999