



Technical datasheet.

Product: Breather PES 300g/m2

Properties	Standard	Unit	Value	Tolerance
Weight	EN 965	g/m ²	300	- 0% + 20%
Thickness at 2 kPa	EN 963-1	mm	2,5	Min 2,0 Max.
Grab test MD	DIN 53 858	N	600	- 20%
Grab test CD	DIN 53 858	N	900	- 20%
Grab Elongation MD at 100N	DIN 53 858	%	25	
Grab Elongation CD at 100N	DIN 53 858	%	25	
Fibre bonding	Needlepunched			
Fibre blend	100% Polyester			

Above technical values are average values from measurements in laboratory.
The right is reserved to make changes without notice at any time

11.08.08